Test Report

Glass Mosaic

327X327mm(Sheet size) 20X20mm(Chip size)

No.	Test Items	Unit	Technical Requirements	Test Results	Decision
1	Sheet size	mm	327±2	325.6~327.6	pass
2	Chip size	mm	Edge length 20±0.5	19.7~20.1	pass
			Thickness	3.7~4.1	----
3	Line	mm	2.5±0.6	2.0~3.0	pass
4	Periphery distance	mm	1~8	2.6~7.7	pass
5	Surface quality	----	It should meet the requirement of the standards in Table 3	Conformed	pass
6	Color	----	All glass mosaic should be the same color basically	Conformed	pass
7	Bond between glass mosaic and paper	----	No falling off	Conformed	pass
8	Time for paper coming off	----	No falling off after 5min	No falling off	pass
		%	≥70 after 40min	100	
9	Thermal stability	----	90° C(30min) 18° C ~25° C (10min) 3 cycles No crack or damage	Conformed	pass
10	Chemical stability	%	Hydrochloric Acid (1mol/L),100 ° C, 4h, K ≥ 99.90	K=99.93	pass
			Sulfuric acid(1mol/L),100 ° C ,4h, K≥99.93	K=99.95	
			Sodium hydroxide(1mol/L),100 ° C, 1h, K≥99.88	K=99.90	
			Distilled water 100° C, 4h, K ≥99.96	K=99.99	

For and on behalf of
LOUIS VALENTINO (INNER

11	Internal exposure index IRa (Decorative materials)	----	Type A: IRa≤1.0	0.2	Type A
			Type B: IRa≤1.3		
	External exposure index Ir (Decorative materials)	----	Type A: Ir≤1.3	0.3	
			Type B: Ir≤1.9		
			Type C: Ir≤2.8		

For and on behalf of
LOUIS VALENTINO (INNER MONGOLIA) CERAMIC CO.,LTD

Authorized Signature(s)

ONGOLIA) CERAMIC CO.,LTD

uthorized Signature(s)